



*Servizi  
Rappresentanze  
Consulenza  
Progettazione  
Produzione  
Forniture*

ELGA di Gallione Franco  
via del Giglio n°65/B  
55049 Viareggio (LU) ITALIA  
tel. +39 0584 944868  
fax. +39 0584 944851  
E-mail: [fgallione@tiscali.it](mailto:fgallione@tiscali.it)

web: [www.elgaitalia.com](http://www.elgaitalia.com) - Codice NATO Costr: / Forn. (N/CAGE): **AD 010**  
P.IVA 01868240464 - Cod. Fisc. GLL FNC 53P02 L833R - Iscr. C.C.I.A.A. Lucca n°177644

## Scheda Tecnica tessuto per arcate pneumatiche P/n. 0000215

**Basic fabric** : Polyester 1100 dtex 10 x 10 fils/cm

**Coating** : Hypalon/neoprene

Specifications	Test method	Way	Value
Surfacic Mass	NFG 37 102		> 800 g/m <sup>2</sup>
Tensile Strenght	NFG 37 103	WP FP	> 275 daN/5 cm > 275 daN/5 cm
Tear Resistance (Tongue Test)	NFG 37 128/A	WP FP	> 12 daN/5 cm > 10 daN/5 cm
Permeability (Helium) Zeppelin Test	NFG 37114		< 3 l/m <sup>2</sup> /24h
Peeling Test Adhesion	NFT 46 008		> 2 daN/5cm
Cold resistance	NFG 37 111		< -30°C
Heat Aging 7 days at 158°F (70°C)	NFG 37 105		Mechanical propriety unchanged
Hydrocarbon Resistance	NFJ 37 825		Mechanical propriety unchanged
Warp/Weft distorsion	NFG 37 119/1		80% < 3 cm max 5 cm

Standard width	145 cm (edge cut)
Colour standard	Light grey / grey Neptune / white